


Core Data Sheet

Part Number: G56A-85

Core Dimensions:

Uncoated (tol. +/-0.25)		After coating	
OD (mm)	33.02	(max)	33.67
ID (mm)	19.94	(min)	19.29
HT (mm)	10.67	(max)	11.32



Physical Characteristics:			
Winding area (cm ²)	2.97	Strength (N) typ.	472.0
Surface area (cm ²)	49.46	Weight (grams) typ.	42.96
Coating	Epoxy, Light Blue, 0.2 mm approx. per surface. Voltage breakdown 500Vac.		
Packing	Not available.		
Material:			
Grade	85		
Initial Permeability (μi)	125	tol +/-	10
Description	High Flux - gas atomized 80 /20 nickel-iron alloy powder		
Electrical Data:		Magnetic Dimensions:	
AL norm (nH)	127.00	C1 (mm-1)	1.2335
AL max. (nH)	137.16	Le (mm)	79.8
AL min. (nH)	116.84	Ae (mm ²)	64.7
DC bias at 0.8μi (Oe) typ.	35	Ve (mm ³)	5157.8
Power Losses (mW/cm ³) typ. 50kHz, 1000gauss			600
Total Losses (ohms/H/μi) typ. < 20gauss			0.0
Special Comments			
1.			
2.			
3.			

Note: the right to change specification data as required without notice is reserved.

