


Core Data Sheet

Part Number: G29 - 96

Core Dimensions:

Uncoated (tol. +/-0.25)		After coating
OD (mm)	20.32	(max) 20.97
ID (mm)	12.70	(min) 12.05
HT (mm)	6.35	(max) 7.00



Physical Characteristics:

Winding area (cm ²)	1.17	Strength (N) typ.	175.0
Surface area (cm ²)	18.88	Weight (grams) typ.	9.91
Coating	Epoxy, 0.2 mm approx. per surface. Voltage breakdown 500Vac.		
Packing	Not available.		

Material:

Grade	96
Initial Permeability (μ i)	147 tol +/- 12
Description	MPP - gas atomized 80 /20 nickel-iron alloy powder.

Electrical Data:

AL norm (nH)	81.00
AL max. (nH)	87.48
AL min. (nH)	74.52
DC bias at 0.8 μ i (Oe) typ.	22
Power Losses (mW/cm ³) typ. 50kHz, 1000gauss	400
Total Losses (ohms/H/ μ i) typ. < 20gauss	0.2

Magnetic Dimensions:

C1 (mm-1)	2.2146
Le (mm)	50.0
Ae (mm ²)	22.6
Ve (mm ³)	1129.1

Special Comments

- 1.
- 2.
- 3.

Note: the right to change specification data as required without notice is reserved.