


Core Data Sheet

Part Number: G29-97

Core Dimensions:

Uncoated (tol. +/-0.25)		After coating	
OD (mm)	20.32	(max)	20.97
ID (mm)	12.70	(min)	12.05
HT (mm)	6.35	(max)	7.00



Physical Characteristics:

Winding area (cm ²)	1.17	Strength (N) typ.	175.0
Surface area (cm ²)	18.88	Weight (grams) typ.	10.04
Coating	Epoxy, 0.2 mm approx. per surface. Voltage breakdown 500Vac.		
Packing	Not available.		

Material:

Grade	97		
Initial Permeability (μi)	160	tol +/-	12
Description	MPP - gas atomized 80 /20 nickel-iron alloy powder.		

Electrical Data:

AL norm (nH)	87.00		
AL max. (nH)	93.96		
AL min. (nH)	80.04		
DC bias at 0.8μi (Oe) typ.	20		
Power Losses (mW/cm ³) typ. 50kHz, 1000gauss	400		
Total Losses (ohms/H/μi) typ. < 20gauss	0.2		

Magnetic Dimensions:

C1 (mm-1)	2.2146
Le (mm)	50.0
Ae (mm ²)	22.6
Ve (mm ³)	1129.1

Special Comments

- 1.
- 2.
- 3.

Note: the right to change specification data as required without notice is reserved.

