


Core Data Sheet

Part Number: G60-98

Core Dimensions:

Uncoated (tol. +/-0.25)	After coating	
OD (mm) 12.70	(max)	13.35
ID (mm) 7.62	(min)	6.97
HT (mm) 4.75	(max)	5.40



Physical Characteristics:

Winding area (cm ²)	0.40	Strength (N) typ.	87.0
Surface area (cm ²)	7.59	Weight (grams) typ.	3.12
Coating	Epoxy, 0.2 mm approx. per surface. Voltage breakdown 500Vac.		
Packing	Not available.		

Material:

Grade	98		
Initial Permeability (μi)	173	tol +/-	12
Description	MPP - gas atomized 80 /20 nickel-iron alloy powder.		

Electrical Data:

AL norm (nH)	79.00
AL max. (nH)	85.32
AL min. (nH)	72.68
DC bias at 0.8μi (Oe) typ.	18
Power Losses (mW/cm ³) typ. 50kHz, 1000gauss	400
Total Losses (ohms/H/μi) typ. < 20gauss	0.2

Magnetic Dimensions:

C1 (mm-1)	2.6940
Le (mm)	30.6
Ae (mm ²)	11.3
Ve (mm ³)	346.9

Special Comments

- 1.
- 2.
- 3.

Note: the right to change specification data as required without notice is reserved.