



Sailcrest Magnetics Material Group.

Core Data Sheet

Part Number: G22-72

Core Dimensions:

Before coating(tol. +/-0.25)

OD(mm) 6.35

ID(mm) 2.79


HD(mm) 2.79

Aftercoating

(max)7.19

(min)2.09

(max)3.63



Physical Characteristics:

Winding area(cm²) 0.04

Surface area(cm²) 1.76

Probably Weight(g) 0.393

Coating Epoxy.dark black,0.2mm approx .per surface.Voltage breakdown 500Vac

Packing Not available

Material:

Grade 72

Initial Permeability(ui) 26

AL(nH) 10+/-8%

Description SENDUST CORE

Eletrical Data:

AL norm(nH) 10.00

AL max(nH) 10.88

AL min(nH) 9.20

Magnetic Dimensions:

C₁(cm⁻¹) 28.957

Le(cm) 1.361

Ae(cm²) 0.047

Ve(cm³) 0.064

Special Comments

- 1.
- 2.
- 3.

Note:the right to change specification as required without notice is reserved

