




Sailcrest Magnetics Material Group.

Core Data Sheet

Part Number: G22-75

Core Dimensions:

Before coating(tol. +/-0.25)	Aftercoating
OD(mm) 6.35	(max)7.19
ID(mm) 2.79	(min)2.09
HD(mm) 2.79	(max)3.63



Physical Characteristics:

Winding area(cm ²) 0.04	Surface area(cm ²) 1.76
Probably Weight(g) 0.393	
Coating Epoxy.dark black,0.2mm approx .per surface.Voltage breakdown 500Vac	
Packing Not available	

Material:

Grade 75	
Initial Permeability(ui) 125	
AL(nH) 50+/-8%	
Description SENDUST CORE	

Eletrical Data:

AL norm(nH) 50.00
AL max(nH) 54.00
AL min(nH) 46.00

Magnetic Dimensions:

C _l (cm ⁻¹) 28.957
Le(cm) 1.361
Ae(cm ²) 0.047
Ve(cm ³) 0.064

Special Comments

- 1.
- 2.
- 3.

Note:the right to change specification as required without notice is reserved

