



Sailcrest Magnetics Material Group.

Core Data Sheet

Part Number: G23-73

Core Dimensions:

Before coating(tol. +/-0.25)

OD(mm) 17.30

ID(mm) 9.65


HD(mm) 6.35

Aftercoating

(max)18.23

(min)8.82

(max)7.31



Physical Characteristics:

Winding area(cm²) 0.66

Surface area(cm²) 13.53

Probably Weight(g) 5.90

Coating Epoxy.dark black,0.2mm approx .per surface.Voltage breakdown 500Vac

Packing Not available

Material:

Grade 73

Initial Permeability(ui) 60

AL(nH) 43+/-8%

Description SENDUST CORE

Eletrical Data:

AL norm(nH) 43.00

AL max(nH) 46.44

AL min(nH) 39.56

Magnetic Dimensions:

C_l(cm⁻¹) 17.844

L_e(cm) 4.140

A_e(cm²) 0.232

V_e(cm³) 0.960

Special Comments

- 1.
- 2.
- 3.

Note:the right to change specification as required without notice is reserved

