




Sailcrest Magnetics Material Group.

Core Data Sheet

Part Number: G50-75

Core Dimensions:

Before coating(tol. +/-0.25)	Aftercoating
OD(mm) 10.20	(max)11.00
ID(mm) 5.08	(min)4.37
HD(mm) 3.96	(max)4.80



Physical Characteristics:

Winding area(cm ²)	0.16	Surface area(cm ²)	4.55
Probably Weight(g)	1.46		
Coating	Epoxy.dark black,0.2mm approx .per surface.Voltage breakdown 500Vac		
Packing	Not available		

Material:

Grade	75
Initial Permeability(ui)	125
AL(nH)	66+/-8%
Description	SENDUST CORE

Eletrical Data:

AL norm(nH)	66.00
AL max(nH)	71.28
AL min(nH)	60.72

Magnetic Dimensions:

C _l (cm ⁻¹)	23.800
Le(cm)	2.380
Ae(cm ²)	0.100
Ve(cm ³)	0.238

Special Comments

- 1.
- 2.
- 3.

Note:the right to change specification as required without notice is reserved

