




Sailcrest Magnetics Material Group.

Core Data Sheet

Part Number: G56A-72

Core Dimensions:

Before coating(tol. +/-0.25)	Aftercoating
OD(mm) 33.00	(max)34.03
ID(mm) 19.90	(min)19.10
HD(mm) 10.70	(max)11.81



Physical Characteristics:

Winding area(cm ²)	2.97	Surface area(cm ²)	49.46
Probably Weight(g)	33.7		
Coating	Epoxy.dark black,0.2mm approx .per surface.Voltage breakdown 500Vac		
Packing	Not available		

Material:

Grade	72
Initial Permeability(ui)	26
AL(nH)	28+/-8%
Description	SENDUST CORE

Eletrical Data:

AL norm(nH)	28.00
AL max(nH)	30.24
AL min(nH)	25.76

Magnetic Dimensions:

C _l (cm ⁻¹)	12.128
Le(cm)	8.150
Ae(cm ²)	0.672
Ve(cm ³)	5.480

Special Comments

- 1.
- 2.
- 3.

Note:the right to change specification as required without notice is reserved

