



Sailcrest Magnetics Material Group.

Core Data Sheet

Part Number: G57-73

Core Dimensions:

Before coating(tol. +/-0.25)

OD(mm) 26.90

ID(mm) 14.70


HD(mm) 11.20

Aftercoating

(max)27.90

(min)13.90

(max)12.19



Physical Characteristics:

Winding area(cm²) 1.59

Surface area(cm²) 33.83

Probably Weight(g) 25.50

Coating Epoxy.dark black,0.2mm approx .per surface.Voltage breakdown 500Vac

Packing Not available

Material:

Grade 73

Initial Permeability(ui) 60

AL(nH) 75+/-8%

Description SENDUST CORE

Eletrical Data:

AL norm(nH) 75.00

AL max(nH) 81.00

AL min(nH) 69.00

Magnetic Dimensions:

C_l(cm⁻¹) 9.709

L_e(cm) 6.350

A_e(cm²) 0.654

V_e(cm³) 4.150

Special Comments

- 1.
- 2.
- 3.

Note:the right to change specification as required without notice is reserved

