




Sailcrest Magnetics Material Group.

Core Data Sheet

Part Number: G64-74

Core Dimensions:

Before coating(tol.+/-0.25)	Aftercoating
OD(mm) 6.60	(max)7.44
ID(mm) 2.67	(min)1.96
HD(mm) 4.78	(max)5.74



Physical Characteristics:

Winding area(cm ²)	0.04	Surface area(cm ²)	2.28
Probably Weight(g)	0.771		
Coating	Epoxy.dark black,0.2mm approx .per surface.Voltage breakdown 500Vac		
Packing	Not available		

Material:

Grade	74
Initial Permeability(ui)	75
AL(nH)	62+/-8%
Description	SENDUST CORE

Eletrical Data:

AL norm(nH)	62.00
AL max(nH)	66.96
AL min(nH)	57.04

Magnetic Dimensions:

C _l (cm ⁻¹)	14.815
Le(cm)	1.363
Ae(cm ²)	0.092
Ve(cm ³)	0.125

Special Comments

- 1.
- 2.
- 3.

Note:the right to change specification as required without notice is reserved

